



STUCCO ITALIANO srl

Via Rovereto 20, Costabissara 36030 - Italia
Tel. +39 347 2469500 e-mail: info@stuccoitaliano.it

Technical Data Sheet

STUCCO GRASSELLO

Fine natural mineral lime finish

Name	<i>STUCCO GRASSELLO</i>
Description	Natural mineral lime based covering for fine and very glossy decorative finish on interior surface.
Composition	Aged, finely filtered slaked lime putty, special powdered marble granules sifted and selected according to granule size of 000 = mm. 0.0 ÷ 0.04, water and special additives (no more than 2,5% total in wet volume)
Where to use	All the interior wall and ceiling surfaces, special furniture.
Appearance	Very shiny and smooth with pleasant slight natural shading
Colour	White, but any colour possible from our chart of Colouring System
Packaging	Kg 20 net polyethylene containers



STUCCO ITALIANO srl

Via Rovereto 20, Costabissara 36030 - Italia
Tel. +39 347 2469500 e-mail: info@stuccoitaliano.it

TECHNICAL DATA

Application	by hand, with a steel trowel
Dilution	none: ready-to-use paste
Theoretical Yield	gr/m ² 800 ÷ 850 in three coats
Drying Time	3 hours at 20°C to the touch 20 hours at 20°C below the surface
Application Temp.	min. 5 max 30°C - U.R. < 85 % ca.
Specific Weight	1,450 ± 30 (gr/lt.)
PH after 30 days	11.7 ± 0,20
Coat Thickness	0,80 ÷ 1,10 mm. total 3 coats
Inflammability	Not flammable material
VOC	< 1 gr/liter

The packaged product is guaranteed for 24 months, if stored in the original sealed package and at temperatures between +5°C and +35°C

APPLICATION

It should be applied to solid, clean and mould free plasters prepared smooth.

Already painted surfaces require a thorough brushing down to remove dust and uneven parts.

Where necessary, use a brush or roller to apply a coat of **Deko Primer** or **Universal Primer** (Normal Primer) diluted 1 to 8 with water.

Remove the water from the top of the material. It is added to prevent the material from drying during the storage time.

Properly mix the product before tinting and application.

Apply the first coat with a stainless steel trowel taking care not to leave ridges and making the surface as smooth as possible, consuming about 450-500 grams per sq.m.. Let it dry completely and remove the ridges using a spatula or helping yourself with a light sanding. Dust the surface and apply the second coat making it very smooth and without ridges. Before it dries completely apply the last thin coat and after a while, before it dries, polish it using a clean stainless steel trowel well prepared with the edge of the blade well polished and rounded, not sharp. A final polishing can be done with a non-woven fabric.



STUCCO ITALIANO srl

Via Rovereto 20, Costabissara 36030 - Italia
Tel. +39 347 2469500 e-mail: info@stuccoitaliano.it

The day after it is possible to treat the wall with protective waxes or soap.

SPECIAL EFFECT To obtain a spatulate effect it is recommended to apply the second layer with single small strokes of the trowel alternating a full space to an empty space and returning after a few minutes on the same area to complete the application by putting spatulates of material where we left empty spaces. The last coat will be applied normally.

Vicenza, 9 March 2021

We have drawn up the material presented above to the best of our technical and experiential knowledge. Nevertheless, our suggestions and recommendations are not guaranteed. We reserve the right to make modifications to the present information without previous warning.