

MR. CLAY

Distributed in UK by

Whitson's

CLAYBETON



ClayBeton base colour.

For more information, samples and prices contact:

E-mail
sales@caitwhitson.com

Our Shop
www.caitwhitson.com

Phone
01738 442800

WhatsApp Technical
07771663015

PLASTER APPLICATION PROCESS

Spread a 0.4-0.7 mm layer in your base colour on a section of the wall, matching the size of the PET film you will apply first. For even coverage, use a notch trowel, then smooth with preferred trowel.

After applying the base colour, use a putty knife or trowel to layer the remaining colours to achieve the desired effect. Use embossing tools or special rollers to create texture in some areas. This helps the colours blend seamlessly, resulting in beautiful effects. Do not smooth the moulded surface further to avoid destroying the patterns created.

Next, apply the film. Lightly spray the PET film with water and press it against the plastered surface to ensure good adhesion. Try not to move the film as this may damage the pattern.

Once the film is fixed and no longer sliding, you can start shaping the plaster beneath it. Techniques include: hand pressing using firm motions, rolling vigorously in all directions with a roller, using a metal putty knife. Immediately clean up any spills around the PET film in the corners while the plaster is still wet.

Remove the film after 12 - 24 hours. First gently lift one corner of the film, then slowly peel it off. A properly prepared surface will smooth, soft and naturally reflective.





CLAYTRAVERTINE



The ClayTravertine technique is reminiscent of travertine stone. The technique is achieved using a ClayBeton mix and several pigments.

Follow Us

Mr.Clay_UK

Mr. Clay UK

whitsonsltd

whitsonsltd

MR.CLAY LATEST FORMULA

ClayBeton Decorative Plaster is intended for the decorative finishing of interior walls in residential or commercial premises. The product is vapour permeable and absorbs liquids, making it suitable only for dry areas without direct exposure to water or fats. Additional varnish can be applied to improve durability.

A dry mixture of white clay, marble, cement and technological additives. The components are non-hazardous. Mix with water.

Base colour - grey
Thickness - 4 - 7 mm
25 kg for 7-9 m²

MR. CLAY
Distributed in UK by
Whitson's

